

1-800-790-TPMS (8767)

Fidelity Onionskin

25% Cotton Uncoated Paper
Printing and Handling Hints

Fidelity Onionskin is easy to print on when following these simple hints. It is recommended to pretest all printing procedures prior to press time to ensure the desired results are achieved.

OFFSET INKS: Print Onionskin like any conventional uncoated paper. Due to the very low basis weight, pretest to make sure your particular offset printing press will handle the paper.

HANDLING: Keep Onionskin products wrapped until the moment of printing. It is essential to let the paper acclimate, for a minimum of 24 hours – longer during cold weather – in the press room while still wrapped in mill packaging. Keep Onionskin products covered during drying, between passes and prior to any finishing work. Pressroom conditions should be as close as possible to 68 degrees, and 45-60% relative humidity.

VARNISH: Varnish is optional as a surface protector.

FOLDING AND SCORING: To properly score and fold Onionskin, use a rounded channel score with a 1 or 2 point rule and a 0.030" or 0.040" channel matrix. Score with the grain, using a light letterpress score for maximum control. On large projects with less stringent quality requirements on-press litho-scoring may be acceptable. Fold into the bead of the score. On some projects there will be no need to score this paper at all, as it is very flexible and light.

BINDING: Onionskin is suitable for all standard binding processes. It is important to plan for proper grain direction in all binding applications. Grain direction should run parallel to the spine for optimum results.

LASER AND INKJET: Please pretest on your equipment as this very light paper may not work with some devices.

Note: The above recommendations are "hints" based on our knowledge and experience. The Paper Mill Store .com and its affiliates do not accept responsibility for omissions or pressroom errors.